

A01 Producer

Acciaieria Arvedi



Acciaieria Arvedi S.p.A.
Sede legale:
Viale Enrico Forlanini, 23
20134 Milano

Cap.Soc. € 112.900.000
interamente versato
Società soggetta all'attività di
direzione e coordinamento di
Finarvedi SpA
Società con Socio Unico

Via Acquaviva, 18
26100 Cremona - Italia
Tel. +39 0372 4781
Part.IVA IT 11852670154
Cod.fisc. 00910070192
Reg.Imp.MI 00910070192
REA MI 1497770

A07 Your order

ZZ23003984

B01 Coil NERO 1500,0x2,00 S355MC

B09 Thickness 2,00 mm

B11 Length

B04 Delivery

UNI EN 10149-2-2013

A08 Our confirmation 0311180091/30

Delivery note 326173765 / 30 / 34084403

B10 Width 1.500,0 mm

B02 Steel grade S355MC

A06 Customer

Thyssenkrupp Materials

UL. GRUDZIADZKA 159

TORUN

87-100

K-P

A02 Mill Test - Inspection Certificate

nr. 0001085529 3.1 EN10204

Z02 Date 21.09.2023 EN10168

Via Di Servola, 1
34145 Trieste - Italia

B16	C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	C86	C87	C88	C89	C90	C91	C92
HEAT	C%	Mn%	Si%	P%	S%	C%	Ni%	Mo%	Cu%	Sn%	Al%	TT%	Nb%	V%	B%	N%	Nb%	TT%	C-P%	Cu%	Si%	CEV
	min										0,015						+ Ti%	+ Nb%	+ Mo%	+ Cu%	+ Ni%	
	max	0,12	1,50	0,03	0,025	0,020						0,150	0,09	0,200			0,22					
325508	0,04	0,43	0,03	0,007	0,003	0,05	0,06	0,01	0,16	0,01	0,030	0,001	0,02	0,012	0,0001	0,01	0,03					0,15

B07	B16	B12	C00	C13	C11	C12
BATCH ID	HEAT	NOMINAL WT. KG	A80%	Rp02	Rm	
			%	MPa	MPa	
			min	19	355	430
			max		550	
-73250805	325508	23.660	25	426	468	

C00 Sample identification

D01 Inspection marking, surface appearance and dimensions:

No remark

C30 Hardness test - Test type

Z01 We certify that the product supplied complies with the req.

C02 Testing Directions

Z07 Prismatic test pieces have been used in tensile tests

L Longitudinal

Z05 MS certifications

Company with ISO 9001 and IATF 16949 certified management system

Z02 Validation

NAME
T.FERABOLI

Z03 Insp. agency stamp

Signature



A05 DOCUMENT ORIGINATOR

QUALITY DEPT. ACCIAIERIA ARVEDI

MOD-QUA-16 Rev.0 of 20/09/2016

